

LABORATÓRIOS - V.N.FAMALICÃO

COMPANY
FÁBRICA ARTESANAL TAPETES BEIRIZ II, LDA.
RUA COMENDADOR BRANDÃO, 484

4495-375- PÓVOA DE VARZIM

Request Nr.: 910/2017

Date of Reception : 2017/01/30

Observations

Samples reference - Your reference

1499/2017 - AVIZ /PORTO /QUEEN /ROYAL /VERSA

Tests required

Burning Behaviour
Wool / Latex

COMMENTS

See last page

- The tests were performed between the following dates: 2017/01/30 and 2017/01/31.

V.N.FAMALICÃO, 31th January 2017

LABORATORY
COORDINATOR



(Engª Suzana Blattmann)

NOTES:

- These results were obtained according to the proceedings referred in the Quality Manual of CITEVE and concern only the samples submitted to testing (above mentioned).
- Any part of this report cannot be reproduced without the prior permission of CITEVE.
- The tests signalled by * are not included in the scope of accreditation of this laboratory
- q.l - quantification limit d.l. - detection limit n.d. - not detected

LABORATÓRIOS - V.N.FAMALICÃO

<u>Sample Ref.</u>	<u>Your ref.</u>	<u>Sample description</u>
1499 /2017	AVIZ /PORTO /QUEEN /ROYAL /VERSA	8 Specimen of carpet

Test/Standard: * SURFACE FLAMMABILITY OF CARPETS AND RUGS / 16 CFR 1630/1631

Results

Shortest distance between the edge of the hole in the flattening frame and the charred area

Individual values (cm) :	9,2
	8,4
	9,2
	7,8
	8,0
	8,2
	8,5
	8,5

Number of specimens in which the charred area does not extend to within 2,54cm of the edge of the hole in the flattening frame :

8

Test Conditions

Conditioning: 2h at 105°C followed by 1h in a desiccator.

State of specimens: As received and conditioning.

COMMENTS

The sample meets the requirements of 16 CFR 1630.
